



Composite Reinforcement Solution

CompoGrid Pavement Reinforcement and Moisture Barrier System is manufactured at a Saint-Gobain ADFORS facility that has achieved ISO 9001:2008 certification, registration #0045662 and meets the requirements of EN 15381. CompoGrid is a composite material consisting of fiberglass reinforcement grid coated in a patent-pending elastomeric polymer, bonded to a spun bond polyester textile. GlasGrid CG100L conforms to the property values listed below, which have been derived from quality conformance testing performed by a GAI-LAP accredited laboratory:

Property	Metric	Imperial	Test Method
Tensile Strength (MD x XD) (Ultimate)	115 x 115 +/- 15 kN/m	655 x 655 +/- 85 lbs/in	ASTM D4595 EN-ISO 10319:2008
Tensile Elongation (Ultimate)	2.5 +/- 0.5%	2.5 +/- 0.5%	ASTM D4595 EN-ISO 10319:2008
Tensile Resistance @ 2% Strain	95 x 95 +/- 20 kN/m	542 x 542 +/- 115 lbs/in	ASTM D4595 EN-ISO 10319:2008
Secant Stiffness EA @ 1% Strain (MD x XD)	4,600 x 4,600 +/- 600 N/mm	26,265 x 26,265 +/- 3,425 lbs/in	ASTM D4595 EN-ISO 10319:2008
Young's Modulus E	73,000 MPa	10.6 x 10 <sup>6</sup> psi	
Mass per Unit Area	441 g/m <sup>2</sup>	13 oz/yd <sup>2</sup>	ASTM D5261-92 ISO 9864
Asphalt Retention	0.45 l/m <sup>2</sup>	0.1 gal/yd <sup>2</sup>	ASTM D6140 EN 15381 Annex C
Melting Point Coating	>232° C	>450° F	ASTM D276/EN-ISO 3146
Melting Point Glass	>820° C	>1508° F	ASTM C338
Roll Length	100 m	328 ft	
Roll Width	1.5 m	5 ft	
Roll Area	150 m <sup>2</sup>	179 yd <sup>2</sup>	
Grid Size (Center to Center of Strand)	25 x 25 mm	1.0 x 1.0 in	
Material	Fiberglass reinforcement with modified polymer coating and bonded to a spun bond polyester textile specifically engineered for asphalt overlays		

The values and tolerances given are obtained in our laboratories and in accredited testing institutions. All imperial values are approximate. The information given in this data sheet is to the best of our knowledge true and correct. However new research and practical experience can make revisions necessary. We reserve the right to make changes at any time. Statements concerning possible use of our product are not intended as recommendations for their use in the infringement of any patent. No patent warranty of any kind, expressed or implied, is made or intended.

**DETAILS OF YOUR UK DISTRIBUTOR**

T: 01525 722200  
E: [info@asphaltrs.co.uk](mailto:info@asphaltrs.co.uk)  
[www.asphaltrs.co.uk](http://www.asphaltrs.co.uk)



Saint-Gobain ADFORS  
[www.glasgrid.com](http://www.glasgrid.com)  
Email: [glasgrid@saint-gobain.com](mailto:glasgrid@saint-gobain.com)

